

No. : TJIN1809013563MR Date : Sep 27, 2018 Page: 1 of 4

# CUSTOMER NAME:HEBEI XINTELI TRADING CO.,LTD.ADDRESS:NO.29 TAIHUA STREET,SHIJIAZHUANG,CHINA

Sample Name : 304 stainless steel stitching wire

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

*****			
SGS Ref. No.	:	TJHL1809005135SD, GZIN1809050405MR	
Date of Receipt	:	Sep 18, 2018	
Testing Start Date	:	Sep 18, 2018	
Testing End Date	:	Sep 27, 2018	
Test result(s)	:	For further details, please refer to the following page(s) (Unless otherwise stated the results shown in this test report refer only to the sample(s) tested)	

Signed for SGS-CSTC Standards Technical Services(Tianjin) Co., Ltd

Mike Wang

Mike Wang Authorized signatory



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <a href="http://www.sgs.com/en/Terms-and-Conditions.asp">http://www.sgs.com/en/Terms-and-Conditions.asp</a> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-and-Condit

Building C-13, No.80, Haiyun Avenue, TEDA, Tianjin, China 300457 t(86-22)5999 5319 f(86-22)5999 5335 www.sgsgroup.com.cn 中国・天津・经济技术开发区海云街80号C-13厂房 邮编:300457 t(86-22)5999 5319 f(86-22)5999 5335 e sgs.china@sgs.com



No. : TJIN1809013563MR Date : Sep 27, 2018 Page: 2 of 4

Summary of Results:


No.	Test Item	Test Method	Result	Conclusion
1	Acetic Acid Salt Spray (AASS) Test	ISO 9227:2017	See results	/

Note: Pass : Meet the requirements;

Fail : Does not meet the requirements;

/: Not Apply to the judgment.

Original Sample Photo:





Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <a href="http://www.sgs.com/en/Terms-and-Conditions.asp">http://www.sgs.com/en/Terms-and-Conditions.asp</a> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-and-Condit

Building C-13, No.80, Haiyun Avenue, TEDA, Tianjin, China 300457 t(86-22)5999 5319 f(86-22)5999 5335 www.sgsgroup.com.cn 中国・天津・经济技术开发区海云街80号C-13厂房 邮编:300457 t(86-22)5999 5319 f(86-22)5999 5335 e sgs.china@sgs.com



No. : TJIN1809013563MR Date : Sep 27, 2018 Page: 3 of 4

Test Item: Acetic Acid Salt Spray (AASS) Test

Sample Description: Metal product

Test Method: ISO 9227:2017

Test Condition:

Concentration of solution collected: (50±5) g/L NaCl

Chamber temperature: (35±2)°C

Volume of salt solution collected: (1.0~2.0) ml/(80cm<sup>2</sup>·h)

pH of collected solution at (25±2)  $^\circ\!\mathrm{C}\colon$  3.1~3.3

Exposure period: 72h

Test Result:

Sample .	Appearance rating				
	#1	#2	#3	General level	
A	10	10	10	10	

Note: Appearance rating refers to EN ISO 10289:2001, as follows:

Area of defects, A (%)	Appearance rating	
0(No defects)	10	
0 <a≤0.1< td=""><td>9</td></a≤0.1<>	9	
0.1 <a≤0.25< td=""><td>8</td></a≤0.25<>	8	
0.25 <a≤0.5< td=""><td>7</td></a≤0.5<>	7	
0.5 <a≤1.0< td=""><td>6</td></a≤1.0<>	6	
1.0 <a≤2.5< td=""><td>5</td></a≤2.5<>	5	
2.5 <a≤5.0< td=""><td>4</td></a≤5.0<>	4	
5.0 <a≤10< td=""><td>3</td></a≤10<>	3	
10 <a≤25< td=""><td>2</td></a≤25<>	2	
25 <a≤50< td=""><td>1</td></a≤50<>	1	
50 <a< td=""><td>0</td></a<>	0	




Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format document, advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's solid responses at Intervention only and within the limits of client's instructions, if any. The Company's solid client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction document. Finds document be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or fails/faction of the comtent or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only. Attention:To check the authenticity of testing / inspection report & certificate, please contact us at telephone:(86-755) 8307 1443, or email: CN.Doccheck@ass.com

Building C-13, No.80, Haiyun Avenue, TEDA, Tianjin, China 300457 t(86-22)5999 5319 f(86-22)5999 5335 www.sgsgroup.com.cn 中国・天津・经济技术开发区海云街80号C-13厂房 邮编:300457 t(86-22)5999 5319 f(86-22)5999 5335 e sgs.china@sgs.com



No. : TJIN1809013563MR Date : Sep 27, 2018 Page: 4 of 4

Test Photo:



Equipment Information:

Equipment	Model	Equipment No.	Calibration date	Next Calibration date
Salt Spray Chamber	TG-2100-M	GZMR-AG-E123	2018-05-14	2019-05-13

Note: The above test was subcontracted.

\*\*\*\*\*\*\*\* End of report\*\*\*\*\*\*\*



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <a href="http://www.sgs.com/en/Terms-and-Conditions.asp">http://www.sgs.com/en/Terms-and-Conditions.asp</a> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-and-Condit

 Building C-13, No.80, Haiyun Avenue, TEDA, Tianjin, China 300457
 t
 (86-22)
 5999
 5319
 f
 (86-22)
 5999
 5335
 www.sgsgroup.com.cn

 中国・天津・经济技术开发区湾云街80号C-13/厂房
 邮编:300457
 t
 (86-22)
 5999
 5319
 f
 (86-22)
 5999
 5335
 e
 sgs.china@sgs.com